

OK Autrod B3 SC

Cr-, Mo-alloyed, copper-coated wire for Submerged Arc Welding. Very low level of impurities. X-bar (Bruscatto-) max. 7. With OK Flux 10.65 for highest toughness requirements also after Step-Cooling; very clean weld metal with X-bar max. 10. Mainly for creep resistant steels (2,25% Cr, 1% Mo).

Classifications Wire Electrode	SFA/AWS A5.23 : EB3R EN ISO 24598-A : S S CrMo2
Approvals	CE EN 13479

Approvals are based on factory location. Please contact ESAB for more information.

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
0.11	0.65	0.10	0.003	0.003	0.08	2.50	1.00	0.006	0.005

Typical Wire Composition %

Cu	Nb	Ti	Sb	As	B	Sn	Mn+Si	Nb+Ti+V	P+Sn	J-Factor	X-bar
0.08	0.006	0.002	0.002	0.003	0.0005	0.003	0.75	0.014	0.006	50	5